



POLYAMIDE EPOXY COATING GLOSS/SEMI-GLOSS V400

Features

- Highly cross-linked film for toughness and durability
- Resists many chemicals and solvents
- Suitable for immersion
- Medium build epoxy

Recommended For

Corotech® V400 Polyamide Epoxy is a multi-use epoxy designed for coating items including tanks, machinery, floors, structural members, walls and other industrial and commercial substrates requiring a durable and resistant finish. The base component dictates the colour of the mixed kit, while the converter determines the gloss and film build level.

General Description

Polyamide Epoxy Coating is a multi-use epoxy designed for tanks, machinery, floors, structural members, walls, boats, and other industrial and commercial substrates requiring a durable coating in severe environments. Floors: moderate- to heavy-duty performance in commercial/industrial environments exposed to heavy foot traffic and occasional traffic of lightweight rubber-tired vehicles, intermittent spillage of mild to heavier chemicals, occasional steam and chemical cleaning. Metal: excellent for use on ferrous metals, non-ferrous metals and galvanized metal. **This is a two component product that requires 1 part of the proper "A" component mixed with 1 part of part "B" catalyst. The components are already premeasured to the proper mix ratio. No measuring required. Do not mix partial kits.**

Limitations

- This product will not cure at surface temperatures below 7.2°C (45°F).
- Do not paint if surface temperature is within 5 degrees of the dew point or if rain is expected within 12 hours.
- This product will amber and chalk if exposed to sunlight.

Product Information

Colours — Standard:

Clear (00), Safety Yellow (10), Safety Red (20), Silver Gray (70), Battleship Gray (75), Black (80), Tintable White (86)

— Tint Bases:

Tintable White (86), Deep Base (87), Clear Base (88)

Tint With Industrial (844 Type) Colorants Only

Tint Part "A" only. Check colour accuracy by mixing equal portions of the "A" & "B" components and allow to dry.

Gloss (90), Semi-Gloss (91), High Build (92)

— Special Colours:

Contact your retailer.

Certification:

The products supported by this data sheet contain a maximum of 340 grams per litre VOC / VOS excluding water & exempt solvents.

This product is compliant as an Industrial Maintenance Coating.

Any "A" with -90 meets performance specs of MIL-C-22750 & MIL-P-25441

Any "A" with -91 meets performance specs of MIL-C-4556 & MIL-C-22750 (Semi-Gloss)

Master Painters Institute MPI # 177 (Semi-Gloss Catalyst)

Master Painters Institute MPI # 82 when used with an anti-slip additive

Master Painters Institute MPI # 98 (High Build Catalyst)

Master Painters Institute MPI # 108 (Gloss Catalyst)

This product has been approved by CFIA (Canadian Food Inspection Agency) for use in Food Processing Facilities.

Technical Assistance:

Available through your local authorized independent Benjamin Moore® retailer. For the location of the retailer nearest you, call 1-877-711-6830, or visit www.benjaminmoore.ca

Technical Data◇

Generic Type	Polyamide Epoxy	
Pigment Type	Titanium Dioxide	
Volume Solids (mixed as recommended)	62% ± 1 (Gloss/Semi-Gloss) 66% ± 1 (High Build)	
Coverage per 3.79 L at Recommended Film Thickness	Gloss/Semi-Gloss 37.2-46.5 sq. m. (400 – 500 Sq. Ft.) High Build 18.6-23.2 sq. m. (200 – 250 Sq. Ft.)	
Recommended Film Thickness	– Wet	Gloss/Semi-Gloss 3.2 – 4.0 mils High Build 6.4 - 8.0 mils
	– Dry	Gloss/Semi-Gloss 2.0 – 2.5 mils High Build 4.2 - 5.3 mils
Depending on surface texture and porosity.		
Dry Time @ 25°C (77 °F)	– To Touch	6 Hours
	– To Recoat	10 - 12 Hours
	– Foot Traffic	24 - 48 hours
	– Full Cure	7 Days
Dries By	Chemical Cure	
Dry Heat Resistance	148.9 °C (300 °F)	
Viscosity @ 25°C (77°F) (mixed as recommended)	75 – 80 KU (Gloss)	
	80 – 85 KU (Semi-Gloss) 85 - 90 KU (High Build)	
Flash Point	Mixed: 26.7°C (80°F). (TT-P-141, Method 4293)	
Gloss / Sheen	Gloss 85 + units @ 15.6°C (60°F)	
	Semi-Gloss 40 - 50 units @ 15.6°C (60°F)	
	High Build 65 - 75 units @ 15.6°C (60°F)	
Surface Temperature at application	– Min.	10 °C (50 °F)
	– Max.	32 °C (90 °F)
Thin With	Do Not Thin	
Clean Up Thinner	Corotech® V704 Epoxy Reducer	
Mixed Ratio (by volume)	1 : 1	
Induction time @ 25 °C (77 °F)	30 Minutes	
Pot Life @ 25 °C (77 °F)	7 Hours	
Weight Per 3.79 L (mixed as recommended)	4.85 – 5.22 kg (10.7 – 11.5 lbs)	
Storage Temperature	– Min.	7.2°C (45°F)
	– Max.	35°C (95°F)

Volatile Organic Compounds (VOC)

326 Grams / Litre*

Catalyst Catalyzed

◇ Reported values are for Tintable White. Contact retailer for values of other bases or colours.

Polyamide Epoxy Coating V400

Surface Preparation

All surfaces must be sound, dry, clean and free of oil, grease, dirt, mildew, mill scale, form release agents, curing compounds, loose and flaking paint and other surface contaminants.

NEW SURFACES: Concrete and Masonry: All masonry surfaces must be allowed to cure a minimum of 30 days before painting. Acid etch or abrasive blast all slick, glazed concrete or concrete with laitance. For acid etching, follow all manufacturer's directions and safety instructions. Rinse thoroughly and allow to dry. Prime concrete with one coat of V155 100% Solids Epoxy Pre-Primer. V156 Moisture Tolerant Epoxy may also be used.

Steel and Ferrous Metals: All direct to metal coatings provide maximum performance over near white metal blasted surfaces (SSPC-SP 10). There are however, situations and cost considerations that may prevent this type of surface preparation from being done. Corotech® Industrial Coatings have been designed to provide protection over less than ideal surfaces. The recommended standard is a commercial blast (SSPC-SP 6). The steel profile after the blast should be 1-2 mils and be jagged in nature. Surfaces must be free of grit dust. The coating should be applied as soon as possible after the blast in order to prevent flash rusting or surface contamination. Hand tool cleaning (SSPC-SP 2) or power tool cleaning (SSPC-SP 3) can be used if blasting is not possible. In areas where adequate surface preparation is not possible the use of V155 100% Solids Epoxy Pre-Primer is recommended. In highly corrosive areas where additional rust inhibitive qualities are required, prime with one coat of V170 Organic Zinc Rich Primer and an acrylic barrier coat prior to applying epoxy coatings.

Galvanized and Non-ferrous Metals: Solvent clean all surfaces. Apply one coat of Corotech® V110 Acrylic Metal Primer or V175 Waterborne Bonding Primer.

Weathered Galvanized: Clean Thoroughly - Apply one coat V155 100% Solid Epoxy Pre-Primer

Previously Painted Surfaces: Can be applied over most old industrial finishes in good condition. Test patches are recommended to check for wrinkling or lifting of existing coatings. V155 100% Solids Epoxy Pre-Primer may be used as a barrier coat over all existing coatings.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by logging onto Health Canada @ http://www.hc-sc.gc.ca/ewh-semt/contaminants/lead-plomb/asked_questions-questions_posees-eng.php

Application

Mixing Instructions:

This is a two component kit and is pre-proportioned for error free mixing. DO NOT vary from these instructions. Mix "A" & "B" separately before combining.

- Carefully combine the entire contents of V400-90, V400-91 or V400-92 activator with the V400-Part A component; scrape the sides of the pail of Part B to make sure all liquid has been added.
- Using a jiffy mixer at low speed, blend this mixture for three to five minutes until completely blended.
- Keep the mixing blade turning at a slow speed to minimize whipping air into material. Scrape sides of pail during the mixing process.
- Care must be taken to assure both components are completely mixed in order to avoid partially cured spots in the coating.
- Allow to induct for 30 minutes.

It is extremely important to remember that Epoxy Coatings have a limited pot life; therefore, it is wise to make sure sufficient manpower and correct application tools are in order prior to starting the mixing sequence. Estimated pot life is: 14 Hrs. @ 10°C (50°F) / 7 Hrs. @ 25°C (77°F) 3 Hrs. @ 38°C (100°F). Do not thin this product – it is ready to use once both components are thoroughly mixed.

Application:

Airless Spray (Preferred Method): Tip range between .015 and .019. Total fluid output pressure at tip should not be less than 2000 psi.

Air Spray (Pressure Pot): DeVilbiss MBC or JGA gun, with 704 or 765 air cap and Fluid Tip E.

Brush: Natural Bristle only.

Roller: Industrial Cover with Phenolic core. 6.35 mm – 12.7 mm (¼" – ½") nap.

NOTE: Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with recommended thinner. No reduction is necessary.

Special Note: To ensure complete clarity of the V400-00 Clear, this item should only be catalyzed with the V400-90 Gloss Converter. The use of the Semi-Gloss Converter will give the V400-00 Clear a hazy look. All painted surfaces may be slippery, especially when wet. Where non-slip properties are required, a non-skid additive such as Corotech V630 should be used.

All epoxy coatings will chalk and fade if applied on exterior surfaces subjected to direct sunlight. All epoxies tend to yellow. Where colour and gloss retention is important, top-coating will be necessary. Will stain with prolonged exposure to some solvents and chemicals or in kennels if exposed to animal waste. This staining will not effect the durability or protective qualities of the coating. Do not apply if material, substrate or ambient temperature is below 7.2 °C (45 °F). Relative humidity should be below 90%. Do not apply if within 5 degrees of dew point or if rain is expected within 12 hours of application.

TEST DATA	
Flexibility (ASTM D1737)	Pass 4.8 mm (3/16") Mandrel
Sag Resistance (w/-90B)	Passes 8+ mils
Sag Resistance (w/-91B)	Passes 8 + mils
Sag Resistance (w/92B)	Passes 16+ mils
Steam Resistance	Yes
Dry Heat Resistance	148.89°C (300°F)
Wet Heat Resistance	65.56°C (150°F)
Adhesion (ASTM D3359)	Pass 5B
Humidity (ASTM D4585) (2 Coats over V150 – 1000 Hours)	Face Corrosion: None Face Blistering: None Rating: 10, Rust: 0.00%
Salt Spray (ASTM B117) (2 Coats over V150 - 1000 Hours)	Face Corrosion: None Face Blistering: None Rating: 10, Rust: 0.00%

CHEMICAL RESISTANCE GUIDE (NON-IMMERSION)	
Fresh Water	Excellent
Salt Water	Excellent
Acids	Good
Alkalis	Good
Solvents	Excellent
Fuel	Good
Acidic Salt Solutions	Excellent
Alkaline Salt Solutions	Excellent
Neutral Salt Solutions	Excellent

SYSTEMS RECOMMENDATIONS	
PRIMERS	
Ferrous Metal (Blasted)	V110 Line, V150 Line, V155-00 or V160 Line
Ferrous Metal (Marginally Prepared)	V155-00 or V160 Line
Non-Ferrous Metal	V110 or V175-00
Concrete	Use Direct or use V110 Line, V155-00, V160 Line, or V400-00 Clear
Aged coatings	Use Direct (Check Compatibility) or use V110 Line as a barrier Coat
COMPATIBLE INTERMEDIATES	
V160 Line	
For substrates other than listed above, or for usage in severe environmental conditions, please consult with Corotech® Technical Service.	

Polyamide Epoxy Coating V400

Clean Up

Clean up with Corotech® V704 Epoxy Reducer.

Environmental Health & Safety Information

Warning!

Causes skin irritation

Causes serious eye irritation

May cause an allergic skin reaction

Suspected of causing cancer

May cause damage to organs through prolonged or repeated exposure

May be fatal if swallowed and enters airways

Flammable liquid and vapor

Prevention: Obtain special instructions before use. Do not handle until all safety precautions have been read and understood. Use personal protective equipment as required. Wash face, hands and any exposed skin thoroughly after handling. Contaminated work clothing should not be allowed out of the workplace. Do not breathe dust /fume /mist /vapors /spray. Keep away from heat /sparks /open flames /hot surfaces, no smoking. Keep container tightly closed. Ground /bond container and receiving equipment. Use explosion-proof electrical /ventilating /lighting /equipment. Use only non-sparking tools. Take precautionary measures against static discharge. Wear protective gloves /protective clothing /eye protection /face protection.

Response: If exposed or concerned get medical attention.

If in eyes rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. If eye irritation persists get medical attention. If skin irritation or rash occurs get medical attention. If on skin (or hair) take off immediately all contaminated clothing. Rinse skin with water. Wash contaminated clothing before reuse. If swallowed immediately call a POISON CENTER or physician. Do NOT induce vomiting. In case of fire use CO₂, dry chemical, or foam for extinction.

Storage: Store locked up. Store in a well-ventilated place. Keep cool.

Disposal: Dispose of contents/container to an approved waste disposal plant.

IMPORTANT: Designed to be mixed with other components. Mixture will have hazards of all components. Before opening packages, read all warning labels. Follow all precautions.

CAUTION: All floor coatings may become slippery when wet. Where non-skid characteristics are desired, a small amount of clean sand may be added. Stir often during application.

This document represents hazards of the product referenced above. Refer to the individual Safety Data Sheet for hazards of the specific product you will be using.

**KEEP OUT OF REACH OF CHILDREN
FOR PROFESSIONAL USE ONLY
NOT FOR RESIDENTIAL USE**

**Refer to Safety Data Sheet for
additional health and safety information.**